

LG PMMA IH830

Polymethyl Methacrylate Acrylic

Technical Data

Product Description

LG PMMA IH830 is a Polymethyl Methacrylate Acrylic material. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of LG PMMA IH830 are:

- Flame Rated
- RoHS Compliant

Typical application of LG PMMA IH830: Automotive

General

Material Status	•Commercial: Active	
Literature 1	• Processing - LG PMMA (English)	
UL Yellow Card 2	•Technical Datasheet (English)	
Availability	•E67171-248633	
Features	•Asia Pacific	•Latin America
Uses	•Europe	•North America
RoHS Compliance	•General Purpose	
Processing Method	•General Purpose	
	•RoHS Compliant	
	•Injection Molding	

Physical	Nominal ValueUnit	Test Method
Density / Specific Gravity	1.18g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	2.3g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.20 to 0.60%	ASTM D955
Water Absorption (24 hr)	0.30%	ASTM D570
Mechanical	Nominal ValueUnit	Test Method
Tensile Strength (Yield)	70.6MPa	ASTM D638
Tensile Elongation (Yield)	13%	ASTM D638
Flexural Modulus	3410MPa	ASTM D790
Flexural Strength (Yield)	135MPa	ASTM D790
Impact	Nominal ValueUnit	Test Method
Charpy Notched Impact Strength	1.4kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	15kJ/m ²	ISO 179/1eU
Notched Izod Impact (Area)	1.50kJ/m ²	ASTM D256
Hardness	Nominal ValueUnit	Test Method
Rockwell Hardness (M-Scale)	98	ASTM D785
Thermal	Nominal ValueUnit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	101°C	ASTM D648
Vicat Softening Temperature	114°C	ASTM D1525 4
CLTE - Flow	6.0E-5cm/cm/°C	ASTM D696
Electrical	Nominal ValueUnit	Test Method
Volume Resistivity	> 1.0E+15ohms-cm	ASTM D257
Dielectric Strength 5	20kV/mm	ASTM D149
Dielectric Constant (60 Hz)	3.10	ASTM D150
Dissipation Factor (60 Hz)	0.050	ASTM D150
Flammability	Nominal ValueUnit	Test Method
Flame Rating	HB	UL 94

LG PMMA IH830

Polymethyl Methacrylate Acrylic

Optical	Nominal ValueUnit	Test Method
Refractive Index	1.490	ASTM D542
Transmittance (3200 μm)	92.0 %	ASTM D1003
Haze (3200 μm)	< 0.10%	ASTM D1003

Notes

- ¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.
- ² A UL Yellow Card contains UL-verified flammability and electrical characteristics. UL Prospector continually works to link Yellow Cards to individual plastic materials in Prospector, however this list may not include all of the appropriate links. It is important that you verify the association between these Yellow Cards and the plastic material found in Prospector. For a complete listing of Yellow Cards, visit the UL Yellow Card Search.
- ³ Typical properties: these are not to be construed as specifications.
- ⁴ Loading 1 (10 N)
- ⁵ 4000 V/sec

LG PMMA IH830

Polymethyl Methacrylate Acrylic

Where to Buy

Supplier

LG MMA Corp.
, South Korea
Web: <http://www.lgmma.com/>

Distributor

Biesterfeld Plastic GmbH

Biesterfeld Plastic GmbH is a Pan European distribution company. Contact Biesterfeld Plastic GmbH for availability of individual products by country.

Telephone: +49-40-32008-0

Web: <http://www.biesterfeld-plastic.com/>

Availability: Algeria, Austria, Belgium, Bosnia and Herzegovina, Bulgaria, Croatia, Cyprus, Czech Republic, Egypt, France, Germany, Greece, Hungary, Italy, Libyan Arab Jamahiriya, Luxembourg, Mauritania, Morocco, Netherlands, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Switzerland, Turkey

Chase Plastic Services, Inc.

Chase Plastics Services is a North American distributor with representatives throughout the region. Please find your rep here: <http://www.chaseplastics.com/contact/locations>

Telephone: 800-232-4273

Web: <http://www.chaseplastics.com/>

Availability: North America

POLYMIX

Telephone: +33-3-8920-1380

Web: <http://www.polymix.eu/>

Availability: France, Romania, Tunisia

Resin Resource, Inc.

Telephone: 877-652-3431

Web: <http://www.resinresourceinc.com/>

Availability: North America

Southland Polymers

Southland Polymers - Full Service Engineering and Commodity Resin Distribution Since 1979

Telephone: 562-921-0444

Web: <http://www.southlandpolymers.com/>

Availability: Central America, North America, South America

Telko Oy

Telko Oy is a Pan European distribution company. Contact Telko Oy for availability of individual products by country.

Telephone: +358-9-5211

Web: <http://www.telko.com/>

Availability: Belarus, Denmark, Estonia, Finland, Latvia, Lithuania, Norway, Poland, Russian Federation, Sweden, Ukraine